# Reef Pro — **Ultrafabrics**



624-1413 Octopus



624-2632 Beluga

624-5288 Squid

624-3536 Lionfish



624-1408 Lobster

624-2627 Captain

624-4392 Algae



# Reef Pro from Ultrafabrics

# **Application**

Interior Upholstery

# **General Specifications**

# Composition:

100% Polycarbonate Polyurethane Surface 65% Polyester, 35% Rayon Backing

### Weight:

Approx. 18.2 oz. Per Linear Yard Approx. 12.1 oz. Per Square Yard Approx. 410 Grams Per Square Metre

#### Thickness:

Approx. 1.15 Millimetres

#### Width:

54 Inches / 137 Centimetres

# Repeat:

None

#### **Performance**

# Abrasion:

ASTM D4157 / 400,000 Double Rubs (Wyzenbeek)\*
BS EN ISO 12947-2 / 200,000 Rubs (Martindale)\*
\*meets or exceeds

#### Hydrolysis:

16 Weeks

ASTM D3690 Sect. 6.11 (Hydrolytic Stability) ISO 1419 Method C (Accelerated Ageing)

Adhesion of Coating: ASTM D751

Tear Strength: ASTM D2261

Breaking Strength: ASTM D751

Tensile Strength: BS EN ISO 1421

### Colorfastness

Light: AATCC 16.3, 200 Hours, Grade 4
ISO 105 B02, Grade 6
Crocking: AATCC 8, Grade 4-5 Wet & Dry

# Flammability Requirements

- · ASTM E84 (Adhered) Class A
- CA TB 117-2013 Pass
- FMVSS 302 & 95/28 Annex IV Pass
- NFPA 260 Class 1
- UFAC Class 1

These fabrics, when treated and/or used with other compatible furniture components, have been shown to perform under the fire test conditions of:

ASTM E84 (Unadhered)IMO FTPC Part 8

 BS 5852 Source 0, 1 & 5 (Cig, Match & Crib 5)

• BS EN 1021 Parts 1 & 2

#### **Reef Pro Resists:**

- Ballpoint ink
- Blood
- Mustard and Ketchup
- Betadine
- Denim\*
- Red Wine
- \* Removal of denim dye may vary depending on the period of time the stain sets in. While Pro offers excellent protection, full removal is not guaranteed.

For more information on certifications and standards, sustainability, as well as cleaning and care instructions, please visit our website.







